

## TRANSMITTAL LETTER TO THE UNITED STATES

198487US0XPCT

DESIGNATED/ELECTED OFFICE (DO/EO/US)

U.S. APPLICATION NO. (IF KNOWN, SEE 37 CFR

CONCERNING A FILING UNDER 35 U.S.C. 371

09/674498

INTERNATIONAL APPLICATION NO.

INTERNATIONAL FILING DATE

PRIORITY DATE CLAIMED

PCT/JP00/01386

08 March 2000

10 March 1999

TITLE OF INVENTION

PROPYLENE-BASED RESIN COMPOSITION AND AUTOMOTIVE INTERIOR TRIM

APPLICANT(S) FOR DO/EO/US

Ryuzo TOMOMATSU, et al.

Applicant herewith submits to the United States Designated/Elected Office (DO/EO/US) the following items and other information:

1. ☒ This is a **FIRST** submission of items concerning a filing under 35 U.S.C. 371.
2. ☐ This is a **SECOND** or **SUBSEQUENT** submission of items concerning a filing under 35 U.S.C. 371.
3. ☒ This is an express request to begin national examination procedures (35 U.S.C. 371(f)) at any time rather than delay examination until the expiration of the applicable time limit set in 35 U.S.C. 371(b) and PCT Articles 22 and 39(1).
4. ☐ A proper Demand for International Preliminary Examination was made by the 19th month from the earliest claimed priority date.
5. ☒ A copy of the International Application as filed (35 U.S.C. 371 (c) (2))
  - a. ☐ is transmitted herewith (required only if not transmitted by the International Bureau).
  - b. ☒ has been transmitted by the International Bureau.
  - c. ☐ is not required, as the application was filed in the United States Receiving Office (RO/US).
6. ☒ A translation of the International Application into English (35 U.S.C. 371(c)(2)).
7. ☒ A copy of the International Search Report (PCT/ISA/210).
8. ☒ Amendments to the claims of the International Application under PCT Article 19 (35 U.S.C. 371 (c)(3))
  - a. ☐ are transmitted herewith (required only if not transmitted by the International Bureau).
  - b. ☐ have been transmitted by the International Bureau.
  - c. ☐ have not been made; however, the time limit for making such amendments has NOT expired.
  - d. ☒ have not been made and will not be made.
9. ☐ A translation of the amendments to the claims under PCT Article 19 (35 U.S.C. 371(c)(3)).
10. ☒ An oath or declaration of the inventor(s) (35 U.S.C. 371 (c)(4)).
11. ☐ A copy of the International Preliminary Examination Report (PCT/IPEA/409).
12. ☐ A translation of the annexes to the International Preliminary Examination Report under PCT Article 36 (35 U.S.C. 371 (c)(5)).

## Items 13 to 18 below concern document(s) or information included:

13. ☐ An Information Disclosure Statement under 37 CFR 1.97 and 1.98.
14. ☐ An assignment document for recording. A separate cover sheet in compliance with 37 CFR 3.28 and 3.31 is included.
15. ☒ A **FIRST** preliminary amendment.  
A **SECOND** or **SUBSEQUENT** preliminary amendment.
16. ☐ A substitute specification.
17. ☐ A change of power of attorney and/or address letter.
18. ☐ Certificate of Mailing by Express Mail
19. ☒ Other items or information:

Request for Consideration of Documents Cited in International Search Report

Notice of Priority

PCT/IB/304

PCT/IB/308

U.S. APPLICATION NO. (IF KNOWN, SEE 37 CFR <b>09/674498</b> )	INTERNATIONAL APPLICATION NO. PCT/JP00/01386	ATTORNEY'S DOCKET NUMBER 198487US0XPCT
--	---	---

20. The following fees are submitted.

**BASIC NATIONAL FEE (37 CFR 1.492 (a) (1) - (5)) :**

- ☒ Search Report has been prepared by the EPO or JPO ..... \$860.00
- ☐ International preliminary examination fee paid to USPTO (37 CFR 1.482) ..... \$690.00
- ☐ No international preliminary examination fee paid to USPTO (37 CFR 1.482) but international search fee paid to USPTO (37 CFR 1.445(a)(2)) ..... \$710.00
- ☐ Neither international preliminary examination fee (37 CFR 1.482) nor international search fee (37 CFR 1.445(a)(2)) paid to USPTO ..... \$1000.00
- ☐ International preliminary examination fee paid to USPTO (37 CFR 1.482) and all claims satisfied provisions of PCT Article 33(2)-(4) ..... \$100.00

**ENTER APPROPRIATE BASIC FEE AMOUNT =****CALCULATIONS PTO USE ONLY**

\$860.00

Surcharge of \$130.00 for furnishing the oath or declaration later than ☐ 20 ☐ 30 months from the earliest claimed priority date (37 CFR 1.492 (e)).

**\$0.00**

CLAIMS	NUMBER FILED	NUMBER EXTRA	RATE
Total claims	3 - 20 =	0	x \$18.00
Independent claims	1 - 3 =	0	x \$80.00

\$0.00

\$0.00

Multiple Dependent Claims (check if applicable). ☐**\$0.00****TOTAL OF ABOVE CALCULATIONS =**

\$860.00

Reduction of 1/2 for filing by small entity, if applicable. Verified Small Entity Statement must also be filed (Note 37 CFR 1.9, 1.27, 1.28) (check if applicable). ☐

**\$0.00****SUBTOTAL =**

\$860.00

Processing fee of \$130.00 for furnishing the English translation later than ☐ 20 ☐ 30 months from the earliest claimed priority date (37 CFR 1.492 (f)).

+

**\$0.00****TOTAL NATIONAL FEE =**

\$860.00

Fee for recording the enclosed assignment (37 CFR 1.21(h)). The assignment must be accompanied by an appropriate cover sheet (37 CFR 3.28, 3.31) (check if applicable). ☐

**\$0.00****TOTAL FEES ENCLOSED =**

\$860.00

Amount to be refunded

\$

charged

\$

☒ A check in the amount of \$860.00 to cover the above fees is enclosed.

☐ Please charge my Deposit Account No. \_\_\_\_\_ in the amount of \_\_\_\_\_ to cover the above fees.  
A duplicate copy of this sheet is enclosed.

☒ The Commissioner is hereby authorized to charge any fees which may be required, or credit any overpayment to Deposit Account No. **15-0030** A duplicate copy of this sheet is enclosed.

**NOTE:** Where an appropriate time limit under 37 CFR 1.494 or 1.495 has not been met, a petition to revive (37 CFR 1.137(a) or (b)) must be filed and granted to restore the application to pending status.

SEND ALL CORRESPONDENCE TO:

**22850**

Surinder Sachar  
Registration No. 34,423

SIGNATURE

Norman F. Oblon

NAME

24,618

REGISTRATION NUMBER

Nov. 10 2000

DATE

422 Rec'd PCT/PTO 13 NOV 2000

IN THE UNITED STATES PATENT & TRADEMARK OFFICE

IN RE APPLICATION OF :  
RYUZO TOMOMATSU ET AL : ATTN: APPLICATION DIVISION  
SERIAL NO: NEW APPLICATION :  
(Based on PCT/JP00/01386)  
FILED: HEREWITH :  
FOR: PROPYLENE-BASED RESIN :  
COMPOSITION AND  
AUTOMOTIVE INTERIOR TRIM

PRELIMINARY AMENDMENT

ASSISTANT COMMISSIONER FOR PATENTS  
WASHINGTON, D.C. 20231

SIR:

Prior to examination on the merits, please amend the above-identified application as follows.

## IN THE ABSTRACT

Page 18 (Abstract), please replace the Abstract with the substitute Abstract attached herewith.

IN THE SPECIFICATION

Page 3, line 11, change "80 to 88%" to --78 to 88%--.

Page 4, line 24, change "0.31" to --0.01--.

IN THE CLAIMS

Please amend the claims as follows:

Claim 3, line 2, delete "or 2".

00E777 8644/960

[illegible]

Respectfully submitted,

*D. J. P.*

Daniel J. Pereira, Ph.D.  
Registration No. 45,518



22850

(703) 413-3000  
Fax #: (703)413-2220  
DJPER/la  
I:\user\DJPER\198487-pr.wpd

ABSTRACT

A propylene-based resin composition has good external appearance due to good weld appearance and low gloss and has excellent mechanical properties such as impact resistance and stiffness. The composition is well-balanced in the external appearance and mechanical properties. Automotive interior trims made of the composition are also described. The propylene-based resin composition comprises (A) 60 to 90% by weight of a propylene-based resin (1) comprising 78 to 88% by weight of 23°C p-xylene insolubles (a) and 12 to 22% by weight of 23°C p-xylene solubles (b), (2) the insolubles (a) having an isotactic pentad fraction of 95% or higher, a relaxation time ( $\tau$ ) of 0.01 to 0.35 second at an angular frequency ( $\omega$ ) of 10°/sec when measured by melt viscoelastometry and a molecular weight distribution index (PDI) of 1 to 18 which is expressed by  $\omega_2/10\omega_1$  wherein  $\omega_1$  is an angular frequency at which a storage modulus ( $G'$ ) as measured by melt viscoelastometry is  $2 \times 10^2$  Pa and  $\omega_2$  is an angular frequency at which a storage modulus ( $G'$ ) as measured by melt viscoelastometry is  $2 \times 10^4$  Pa, and (3) the solubles (b) having an intrinsic viscosity  $[\eta]$  (in decalin at 135°C) of 3.3 dl/g or higher and an ethylene unit content of 43% by weight or smaller; (B) 0 to 10% by weight of a rubberlike elastomer; and (C) 10 to 30% by weight of talc. The automotive interior trims are produced by injection-molding the composition.--

## DESCRIPTION

PROPYLENE-BASED RESIN COMPOSITION AND  
AUTOMOTIVE INTERIOR TRIM

5

TECHNICAL FIELD

The present invention relates to propylene-based resin compositions and automotive interior trims such as instrument panels made of the compositions, and more particularly, to propylene-based resin compositions excellent in external appearance such as good weld appearance and low gloss, excellent in mechanical properties such as impact resistance and stiffness, and well-balanced in these properties, and also to automotive interior trims made of the compositions.

15 BACKGROUND ART

With recent tendency toward non-coating finish of automotive interior trims such as instrument panels for the purpose of reducing the production costs, there are rapidly growing demands for developing interior parts having excellent appearance such as good weld appearance and low gloss giving relaxed feeling by preventing light reflection. Also, the demands for safeguard and low-cost materials are coming more severe. In addition, the recent tendency to produce whole parts of instrument panels from the same material creates demand for materials well-balanced in impact resistance and stiffness so as to meet the performance requirements of any parts of instrument panels.

Conventionally, low-cost, general-purpose propylene-based resins have been widely used as materials for automotive interior trims. It is known that the impact resistance (room-temperature Izod impact strength) of propylene-based resins can be effectively improved by blending a styrene-based elastomer. However, the use of styrene-based elastomer causes problems such as increased production cost and high gloss of molded articles.

As molding materials having an excellent low-temperature impact resistance, there have been proposed, for example, a resin composition obtained by blending a crystalline propylene-ethylene block copolymer with an ethylene- $\alpha$ -olefin copolymer produced in the presence of a metallocene catalyst (Japanese Patent Application Laid-Open Nos. 7-145272 and 7-145298); a resin composition obtained by blending a propylene-based resin with an ethylene-butene-1 copolymer having a relatively large butene-1 unit content (produced substantially in the presence of a metallocene catalyst) (Japanese Patent Application Laid-Open Nos. 6-192506 and 7-18151); and a resin composition obtained by blending a propylene-based resin with an ethylene-octene-1 copolymer having a relatively large octene-1 unit content (produced substantially in the presence of a metallocene catalyst) (International Publication No. WO94/6859). These resin compositions exhibit a good low-temperature impact resistance, but fail to produce molded articles having a sufficiently low gloss.

Thus, the propylene-based resin compositions used as materials for automotive interior trims are required to simultaneously satisfy the antinomic characteristics, i.e., mechanical properties such as impact resistance and stiffness and external appearance. The conventional propylene-based resin compositions have been improved in the balance of these properties to some extent, but are still unsatisfactory.

#### DISCLOSURE OF THE INVENTION

The present invention has been made to solve the above problems.

Thus, an object of the present invention is to provide resin compositions having excellent mechanical properties such as impact resistance and stiffness as well as good external appearance such as good weld appearance and low gloss, and being remarkably well-balanced in the external appearance and the mechanical properties. It is another object of the present invention to provide automotive interior trims such as instrument panels which are produced by



injection-molding the compositions.

As a result of extensive studies for solving the above problems, the present inventors have found that resin compositions capable of achieving the above objects are obtained by blending a propylene-based resin having specific properties with talc and optionally a rubber-like elastomer at a particular mixing ratio. The present invention has been accomplished based on this finding.

Thus, a propylene-based resin composition of the present invention comprises:

- (A) 60 to 90% by weight of a propylene-based resin,
  - (1) comprising 80 to 88% by weight of 23°C p-xylene insolubles (a) and 12 to 22% by weight of 23°C p-xylene solubles (b),
  - (2) the insolubles (a) having an isotactic pentad fraction of 95% or higher, a relaxation time ( $\tau$ ) of 0.01 to 0.35 second at an angular frequency ( $\omega$ ) of 10°/sec when measured by melt viscoelastometry and a molecular weight distribution index (PDI) of 1 to 18 which is expressed by  $\omega_2/10\omega_1$  wherein  $\omega_1$  is an angular frequency at which a storage modulus ( $G'$ ) as measured by melt viscoelastometry is  $2 \times 10^2$  Pa and  $\omega_2$  is an angular frequency at which a storage modulus ( $G'$ ) as measured by melt viscoelastometry is  $2 \times 10^4$  Pa, and
  - (3) the solubles (b) having an intrinsic viscosity  $[\eta]$  (in decalin at 135°C) of 3.3 dl/g or higher and an ethylene unit content of 43% by weight or smaller;
- (B) 0 to 10% by weight of a rubber-like elastomer; and
- (C) 10 to 30% by weight of talc.

Further, automotive interior trims of the present invention are produced by injection-molding the above propylene-based resin composition.

#### BEST MODE FOR CARRYING OUT THE INVENTION

The propylene-based resin used as the component (A) of the resin compositions according to the present invention has the following properties.

When treated with p-xylene at 23°C, the component (A) is fractionated

into 78 to 88% by weight of p-xylene insolubles (a) and 12 to 22% by weight of p-xylene solubles (b). When the content of p-xylene insolubles is less than 78% by weight, resultant molded articles are insufficiently balanced in impact resistance and stiffness. When the content of p-xylene insolubles is more than 88% by weight, resultant molded articles fail to show good weld appearance and sufficiently low gloss. The fractionation of the component (A) by p-xylene may be conducted by completely dissolving sample resin in p-xylene at 130°C and then cooling the resultant solution to 23°C, thereby fractionating the sample resin into solubles and insolubles.

The insolubles (a) are required to have an isotactic pentad fraction of 95% or higher. The isotactic pentad fraction referred to herein can be obtained from the signals present in the methyl carbon region of  $^{13}\text{C}$ -NMR spectra. When the isotactic pentad fraction is less than 95%, resultant molded articles are insufficient in the balance between impact resistance and stiffness and also poor in scratch resistance. Therefore, it is desirable that the isotactic pentad fraction is 95% or higher.

The insolubles (a) have a relaxation time ( $\tau$ ) of 0.01 to 0.35 second, preferably 0.05 to 0.30 second, more preferably 0.05 to 0.20 second at an angular frequency ( $\omega$ ) of 10°/sec when measured by melt viscoelastometry. A relaxation time ( $\tau$ ) of less than 0.01 second will provide molded articles having an insufficient balance between impact resistance and stiffness. A relaxation time ( $\tau$ ) of more than 0.35 second will fail to produce molded articles having sufficient weld appearance and sufficiently low gloss. In view of the foregoing, the relaxation time ( $\tau$ ) is preferred to be 0.31 to 0.35 second. The relaxation time ( $\tau$ ) referred to herein was calculated by the formula:  $G'/\omega G''$  wherein  $G'$  is storage modulus and  $G''$  is loss modulus obtained by imposing sinusoidal shear strain on a sample at 175°C and an angular frequency ( $\omega$ ) of 10°/sec using a rotary rheometer (System 4 of Rheometrics Co., Ltd.) having a 25 mm  $\phi$  cone plate with a cone angle of 0.1 radian.

The insolubles (a) have a molecular weight distribution index (PDI) of 1

to 18, preferably 5 to 15. PDI is represented by  $\omega_2/10\omega_1$  wherein  $\omega_1$  is an angular frequency at which the storage modulus ( $G'$ ) obtained by melt viscoelastometry is  $2 \times 10^2$  Pa and  $\omega_2$  is an angular frequency at which the storage modulus ( $G'$ ) is  $2 \times 10^4$  Pa. PDI of less than 1 will result in insufficient balance between impact resistance and stiffness of resulting molded articles. When PDI exceeds 18, resultant molded articles show insufficient weld appearance and insufficiently low gloss. Therefore, the molecular weight distribution index (PDI) is preferably 1 to 18. The PDI was obtained through measurement at 175°C under 30% strain using a rotary rheometer (System 4 of Rheometrics Co., Ltd.) having a 25 mm $\phi$  cone plate with a cone angle of 0.1 radian.

In the present invention, in addition to the above properties of the insolubles (a), the solubles (b) of the component (A) are required to have an ethylene unit content of 43% by weight or smaller. An ethylene unit content exceeding 43% by weight will result in insufficiently balanced impact resistance and stiffness, and poor scratch resistance. In view of this and in order to achieve improved balance between external appearance such as weld appearance and low gloss and mechanical properties such as impact resistance and stiffness, the ethylene unit content is preferably 40% by weight or smaller, more preferably 20 to 40% by weight, still more preferably 33 to 39% by weight.

The intrinsic viscosity  $[\eta]$  of the solubles (b) measured in decalin at 135°C is 3.3 dl/g or higher, preferably 3.5 to 4.0 dl/g. An intrinsic viscosity  $[\eta]$  of less than 3.3 dl/g provides molded articles having insufficient weld appearance and insufficiently low gloss. Therefore, the intrinsic viscosity  $[\eta]$  is preferably 3.3 dl/g or higher. When exceeding 4.0 dl/g, resultant resin composition is likely to cause agglomeration during melt kneading.

The propylene-based resin serving as the component (A) preferably has a melt index (MI) of 1 to 100 g/10 min when measured at 230°C under a load of 2.16 kgf (21.2 N). If MI is less than 1 g/10 min, the resin composition will have poor moldability due to low fluidity. When exceeding 100 g/10 min, resultant

molded articles will have deteriorated mechanical properties. In view of the moldability and the balance in mechanical properties, MI is preferably 5 to 70 g/10 min, more preferably 8 to 40 g/10 min. MI referred to herein was measured according to JIS K7210.

5        The method of producing the propylene-based resin as the component (A) is not particularly restricted, and various methods are usable as long as propylene-based resins satisfying the above requirements are produced. For example, the respective components which are separately produced by polymerization may be blended together to prepare the component (A).

Alternatively, propylene-ethylene block copolymers as the component (A) can be produced by multiple-stage polymerization in the presence of a catalyst system comprising a solid component (a) composed of a solid catalyst component (i) comprising magnesium, titanium, halogen atom and an electron donor, and optionally a crystalline polyolefin (ii), an organic aluminum compound (b), and an ordinary electron-donating compound (c).

In the catalyst system to be used for the multi-stage polymerization, the solid catalyst component (a) is composed of the solid catalyst component (i) containing magnesium, titanium, halogen atom and an electron donor, and optionally the crystalline polyolefin (ii). The solid catalyst component (i) can be prepared by contacting a magnesium compound, a titanium compound and an electron donor. The halogen atom is contained in the magnesium compound and/or the titanium compound in the form of a halide.

The magnesium compound may be a reaction product of metal magnesium, halogen and/or a halogen-containing compound, and an alcohol.


25 Although the titanium compound may be any known titanium compound, preferred is a titanium compound with high halogen content, particularly titanium tetrachloride. The titanium compound may be used alone or in combination of two or more.

The electron donor may be selected from the electron-donating  
30 compounds for the component (c). The solid catalyst component (i) may be

prepared by any known methods proposed in Japanese Patent Application Laid-Open Nos. 53-43094, 55-135102, 55-135103, 56-18606, 56-166205, 57-63309, 57-190004, 57-300407 and 58-47003).

The crystalline polyolefin as the optional component (ii) for the solid component (a) includes, for example, C<sub>2</sub>-C<sub>10</sub> α-olefins such as polyethylene, polypropylene, polybutene, poly-4-methyl-1-pentene. These crystalline polyolefins may be prepared by any known methods, for example, by pre-polymerizing propylene in the presence of a combination of the solid catalyst component (i), an organic aluminum compound and optionally an electron-donating compound (pre-polymerization method).

The organic aluminum compound as the component (b) may be represented by the formula (I):



wherein R<sup>1</sup> represents an alkyl group having 3 to 20 carbon atoms or an aryl group having 6 to 20 carbon atoms; X represents a halogen atom; and p represents a number of 1 to 3.

The catalyst system generally contains an electron-donating compound as the component (c). The electron-donating compound may be a compound containing oxygen, nitrogen, phosphorus, sulfur and silicon, and basically a compound capable of improving the stereospecificity of propylene polymers. For example, preferably used are organic silicon compounds, esters, ketones, ethers, thioethers, acid anhydrides and acid halides.

Although Ziegler-type solid catalysts are described above in detail, metallocene catalysts which have attracted special interest recently may be used for producing the propylene-based resins. The propylene-based resin used as the component (A) in the invention can be produced by various methods, for example, produced by multi-stage polymerization in the presence of the catalyst system mentioned above. The polymerization order and the number of the polymerization stages of the multi-stage polymerization may be suitably determined as required. For example, in the initial polymerization (first-

stage polymerization), propylene may be homo-polymerized or co-polymerized (for example, with ethylene and other olefins in an amount of 2% by weight or less) to give a crystalline propylene-based polymer, and in second or later stage, ethylene and propylene may be subjected to random copolymerization, or  
5 ethylene, propylene and other  $\alpha$ -olefins or polyenes may be subjected to random copolymerization.

Upon the polymerization, the components (a) to (c) may be mixed in contact with each other in a predetermined ratio to give a catalyst system, and immediately after the preparation of the catalyst system, the monomers may  
10 be introduced to the reaction vessel, thereby starting the polymerization. Alternatively, the monomers may be introduced after aging the catalyst system for 0.2 to 3 hours. After the polymerization, the reaction mixture may be post-treated in known manners. The resin composition of the present invention may contain one or more propylene-based resins as the component  
15 (A).

The resin composition of the invention contains a rubber-like elastomer as the component (B). Examples of the rubber-like elastomer include polybutadiene, styrene-butadiene copolymer, acrylonitrile-butadiene copolymer, polymers of conjugated diene compounds such as polyisoprene,  
20 ethylene-propylene random copolymer (ethylene-propylene rubber) and ethylene- $C_{4-10}$   $\alpha$ -olefin random copolymer. Of these rubber-like elastomers, preferred are ethylene-propylene random copolymer (ethylene-propylene rubber) and binary copolymer rubbers obtained by randomly copolymerizing ethylene and octene-1.

25 The resin composition of the present invention may contain, as the component (B), an ethylene- $C_{3-18}$   $\alpha$ -olefin copolymer produced in the presence of a metallocene catalyst. The ethylene- $\alpha$ -olefin copolymer has a density of 0.850 to 0.875 g/cm<sup>3</sup>. If the density is lower than 0.850 g/cm<sup>3</sup>, the stiffness of resultant molded articles is insufficient. If the density is larger than 0.875  
30 g/cm<sup>3</sup>, the impact resistance cannot be improved sufficiently. In view of

stiffness and impact resistance of resultant molded articles, the density is more preferably 0.855 to 0.870 g/cm<sup>3</sup>. The melt index (MI) of the ethylene- $\alpha$ -copolymer is 0.01 to 25 g/10 min. MI smaller than 0.01 g/10 min cannot improve the impact resistance of molded articles sufficiently, and molded  
5 articles will likely to have flow marks. MI larger than 25 g/10 min will fail to provide low gloss and sufficient impact resistance in the creped area. In view of impact resistance, low gloss and moldability, MI is preferably 0.01 to 6 g/10 min, more preferably 0.01 to 1 g/10 min. MI referred to herein was measured at 190°C under a load of 2.16 kgf (21.2 N).

10 The C<sub>3-18</sub>  $\alpha$ -olefins used as comonomers of the copolymer include, for example, straight-chain  $\alpha$ -olefins such as butene-1, pentene-1, hexene-1, octene-1, nonene-1, decene-1 and dodecene-1; and branched  $\alpha$ -olefins such as 3-methylbutene-1 and 4-methylpentene-1. Of these comonomers, especially preferred are straight-chain C<sub>4-10</sub>  $\alpha$ -olefins. These  $\alpha$ -olefins can be used either  
15 singly or in combination of two or more. If desired, a diene component, for example, such as dicyclopentadiene, ethylidenenorbornene, 1,4-hexadiene, 1,9-decadiene and vinyl-norbornene may be combinedly used.

The ethylene- $\alpha$ -olefin copolymers as the component (B) may be suitably selected from any commercially available products, for example, ENGAGE  
20 (trade name of The Dow Chemical Company) POEs sold by Dow Chemical Japan Co., Ltd.

The resin composition of the present invention contains talc as the component (C). In view of the properties such as stiffness, impact resistance, scratch-whitening resistance, weld appearance and prevention of uneven gloss,  
25 preferred are talc having an average particle size of 1 to 8  $\mu$ m and an average aspect ratio 4 or larger. Especially preferred are those produced by mechanical grinding in view of the physical properties and the stiffness.

The resin composition of the invention contains 60 to 90% by weight of the propylene-based resin as the component (A), 0 to 10% by weight of the  
30 rubber-like elastomer as the component (B), and 10 to 30% by weight of talc as

the component (C). If the content of the component (A) is smaller than 60% by weight, molded articles have insufficient weld appearance and gloss not sufficiently low in the creped area. In addition, flow marks occur due to poor moldability. If larger than 90% by weight, the impact resistance will be poor.

- 5 The content of the component (B) is preferably 0 to 7% by weight, more preferably 0 to 3% by weight. If the content of the component (B) exceeds the above range, molded articles have insufficient weld appearance and gloss not sufficiently low. If the content of the component (C) is smaller than 10% by weight, molded articles such as instrument panels are deteriorated in
- 10 dimensional accuracy and stiffness. A content larger than 30% by weight results in poor moldability and insufficient weld appearance of molded articles.

- The resin composition of the invention may optionally contain various known additives such as pigments, nucleating agents, weathering agents, antioxidants, antistatic agents, flame retardants, dispersants, etc. The
- 15 method for producing the propylene-based resin composition of the invention is not specifically defined. For example, the components (A) and (C), optional component (B) and the other additives are melt-kneaded in a single-screw extruder, a twin-screw extruder, a Bumbury mixer, a kneader, rolls etc. to give the composition.

- 20 The automotive interior trims of the invention are produced by molding the propylene-based resin composition in any conventional injection-molding methods such as compressed injection-molding and vapor-blowing injection-molding. The automotive interior trims include, for example, instrument panels, door trims, console boxes, etc.

- 25 The invention is described in more detail with reference to the following Examples, which, however, are not intended to restrict the scope of the invention. The physical properties of molded articles produced were measured according to the methods mentioned below.

(1) Melt Index (MI)

- 30 Melt index of each propylene-based resin composition and propylene-



## (2) Izod Impact Strength

### 5 (3) Bending Modulus

#### (4) Weld Appearance

15 (5) Low Gloss

### (6) Isotactic Pentad Fraction

The properties of propylene-based resin were measured according to the methods mentioned above.

## 1. Production of Propylene Block Copolymer (PP-1)

### (1) Preparation of Magnesium Compound

30 A 500-liter glass reactor equipped with a stirrer was fully purged with

nitrogen gas. Then, 97.2 kg of ethanol, 640 g of iodine and 6.4 kg of metal magnesium were charged into the reactor and stirred under reflux to give a solid reaction product. The reaction mixture containing the solid reaction product was dried under reduced pressure to obtain a magnesium compound (solid reaction product).

#### (2) Preparation of Solid Catalyst Component

Into a 500-liter, three-necked glass flask which had been fully purged with nitrogen gas, were charged 30 kg of the magnesium compound (not ground) prepared in (1), 150 liters of purified heptane, 4.5 liters of silicon tetrachloride and 4.3 liters of di-n-butyl phthalate. Stirring the contents of the flask at 90°C, 144 liters of titanium tetrachloride were added, and reacted at 110°C for 2 hours. The solid product formed was isolated and washed with purified heptane at 80°C. Then, 228 liters of titanium tetrachloride were added to further continue the reaction for 2 hours at 110°C. After sufficiently washing with purified heptane, a solid catalyst component was obtained.

#### (3) Pre-treatment prior to Polymerization

Into a 500-liter reactor equipped with a stirrer, were charged 230 liters of purified n-heptane and 25 kg of the solid catalyst component obtained in (2) successively. Then, 0.6 mole of triethyl aluminum and 0.4 mole of dicyclopentyldimethoxysilane were added per one mole of titanium in the solid catalyst component. Next, propylene was introduced into the reactor until the propylene partial pressure reached 0.3 kg/cm<sup>2</sup> G to carry out the reaction at 20°C for 4 hours. After completion of the reaction, the solid catalyst component was washed several times with n-heptane and stirred for 24 hours while blowing carbon dioxide.

#### (4) Polymerization for Producing Propylene Block Copolymer (PP-1)

In the first stage, the solid catalyst component treated in (3) was fed into a 200-liter polymerization reactor (first polymerization reactor) equipped with a stirrer at a feeding rate of 0.6 mmol/hr in terms of Ti, along with 4.0 mmol/kg-PP of triethylaluminum and 0.4 mmol/kg-PP of

dicyclopentyldimethoxysilane, and propylene were polymerized at 85°C under a pressure (total pressure) of 28 kg/cm<sup>2</sup> G. During the polymerization, the feeding rates of ethylene and hydrogen were controlled so that the resulting copolymer had desired ethylene content and molecular weight.

5 Then, the formed powder was continuously discharged out of the first reactor and transferred into a 200-liter polymerization reactor (second polymerization reactor) equipped with a stirrer. In the second reactor, the polymerization was carried out at 70°C under a pressure (total pressure) of 15 kg/cm<sup>2</sup> G, while controlling the feeding rates of propylene, ethylene and  
10 hydrogen so as to produce a copolymer having desired chemical composition and molecular weight. The formed powder was continuously discharged out of the second polymerization reactor and granulated to obtain a propylene block copolymer (PP-1).

## 2. Production of Propylene Block Copolymers (PP-2 to PP-6)

15 The same procedures as in the production of PP-1 were repeated except for changing the blending ratio as shown in Table 1, thereby obtaining propylene block copolymers PP-2 to PP-6.

### Examples 1-4 and Comparative Examples 1-5

Propylene-based resin (A), rubber-like elastomer (B) and talc (C) were  
20 mixed with 1.0 part by weight, based on 100 parts by weight of the total of (A) to (C), of a dark gray pigment (PP-DHH7343, trade name of Dainichi Seika Co., Ltd.). The amount and properties of each of the components (A) to (C) are shown in Tables 1-1 and 1-2 where the weight percentages of the components (A) to (C) are based on the total (100% by weight) of the components (A) to (C)  
25 and the weight percentages of the components (a) and (b) are based on the total (100% by weight) of the components (a) and (b). The mixture was kneaded in a twin-screw kneader to prepare molding materials, which was then injection-molded at a resin temperature of 220°C into test pieces (140 x 140 x 3 mm; creped plates for trims). The results of measurements of the physical  
30 properties and external appearance of the test pieces are shown in Table 1-2.

	Examples				Comparative Examples				
	1	2	3	4	1	2	3	4	5
Propylene-Based Resin									
Kind	PP-1	PP-1	PP-1	PP-1	PP-2	PP-3	PP-4	PP-5	PP-6
wt. %	75	73	69	83	73	73	73	73	73
(a) 23°C p-xylene insolubles									
wt. %	83	83	83	83	83	84	83	83	90
Isotactic pentad fraction (%)	97.3	97.3	97.3	97.3	97.6	97.7	97.5	97.7	97.3
$\tau$ sec	0.12	0.12	0.12	0.12	0.14	0.11	0.14	0.14	0.11
PDI	10	10	10	10	10	10	10	10	10
(b) 23°C p-xylene solubles									
wt. %	17	17	17	17	17	16	17	17	10
Ethylene content (wt. %)	37	37	37	37	48	37	47	56	42
Intrinsic viscosity $[\eta]$ (dl/g)	3.8	3.8	3.8	3.8	3.8	2.8	2.9	2.1	2.9
MI (g/10 min)	9	9	9	9	9	14	13	11	12

	Examples				Comparative Examples				
	1	2	3	4	1	2	3	4	5
(B) Rubber-like Elastomer									
Kind	LL	LL	LL	LL	LL	LL	LL	LL	LL
wt. %	2	4	8	2	4	4	4	4	4
(C) Talc									
wt. %	23	23	23	15	23	23	23	23	23
Physical Properties of Test Pieces									
MI (g/10 min)	13	11	8	12	10	14	14	12	13
IZOD impact strength (kJ/m <sup>2</sup> )	32	58	NB	46	28	33	26	NB	22
Bending Modulus	2980	2660	2460	2300	2740	2650	2730	2530	2950

(MPa)

## External Appearance of Test Pieces

Weld appearance	◎	○ to ◎	○	◎	◎	△	△ to ○	×	×
Low gloss (%)	2.1	2.1	2.2	2.1	2.1	2.4	2.2	2.9	2.5

## Note

LL: metallocene LL (EG-8100 produced by The Dow Chemical Company).

Talc: JM209 (trade name) produced by Asada Seifun Co., Ltd. having an average particle size of 4.2  $\mu\text{m}$  measured by a laser particle size analyzer

5 SALD2000A manufactured by Shimadzu Corporation.

Industrial Applicability

The propylene-based resin compositions of the present invention have good external appearance such as good weld appearance and low gloss as well  
 10 as excellent mechanical properties such as impact resistance and stiffness. Thus, the propylene-based resin compositions are well-balanced between the external appearance and mechanical properties without any adverse affection to each other irrespective of contradictory natures of these properties. Also, the resin composition provides molded articles requiring no coating finish,  
 15 thereby reducing the production costs. Thus, the resin compositions of the present invention are suitable as molding materials for automotive interior trims.

The automobile interior trims made of the resin compositions of the invention have good external appearance such as weld appearance and low  
 20 gloss, and can eliminate finish coatings, thereby reducing production costs. In addition, the automotive interior trims are also excellent in mechanical properties such as impact resistance and stiffness, and well-balanced between the external appearance and the mechanical properties without any adverse affection to each other irrespective of contradictory natures of these properties.  
 25 Therefore, the automotive interior trims of the invention are favorably used as

[illegible]

## CLAIMS

1. A propylene-based resin composition comprising:
- (A) 60 to 90% by weight of a propylene-based resin,
- 5 (1) comprising 78 to 88% by weight of 23°C p-xylene insolubles (a) and 12 to 22% by weight of 23°C p-xylene solubles (b),
- (2) the insolubles (a) having an isotactic pentad fraction of 95% or higher, a relaxation time ( $\tau$ ) of 0.01 to 0.35 second at an angular frequency ( $\omega$ ) of 10°/sec when measured by melt viscoelastometry and a molecular weight
- 10 distribution index (PDI) of 1 to 18 which is expressed by  $\omega_2/10\omega_1$  wherein  $\omega_1$  is an angular frequency at which a storage modulus ( $G'$ ) as measured by melt viscoelastometry is  $2 \times 10^2$  Pa and  $\omega_2$  is an angular frequency at which a storage modulus ( $G'$ ) as measured by melt viscoelastometry is  $2 \times 10^4$  Pa, and
- (3) the solubles (b) having an intrinsic viscosity  $[\eta]$  (in decalin at 135°C)
- 15 of 3.3 dl/g or higher and an ethylene unit content of 43% by weight or smaller;
- (B) 0 to 10% by weight of a rubber-like elastomer; and
- (C) 10 to 30% by weight of talc.
2. The propylene-based resin composition according to claim 1, wherein the solubles (b) has an ethylene unit content of 33 to 39% by weight.
- 20 3. An automotive interior trim produced by injection-molding the propylene-based resin composition of claim 1 or 2.

## ABSTRACT

A propylene-based resin composition has good external appearance due to good weld appearance and low gloss and has excellent mechanical properties such as impact resistance and stiffness. The composition is well-balanced in the external appearance and mechanical properties. Automotive interior trims made of the composition are also described. The propylene-based resin composition comprises (A) 60 to 90% by weight of a propylene-based resin (1) comprising 80 to 88% by weight of 23°C p-xylene insolubles (a) and 12 to 22% by weight of 23°C p-xylene solubles (b), (2) the insolubles (a) having an isotactic pentad fraction of 95% or higher, a relaxation time ( $\tau$ ) of 0.01 to 0.35 second at an angular frequency ( $\omega$ ) of 10°/sec when measured by melt viscoelastometry and a molecular weight distribution index (PDI) of 1 to 18 which is expressed by  $\omega_2/10\omega_1$  wherein  $\omega_1$  is an angular frequency at which a storage modulus ( $G'$ ) as measured by melt viscoelastometry is  $2 \times 10^2$  Pa and  $\omega_2$  is an angular frequency at which a storage modulus ( $G'$ ) as measured by melt viscoelastometry is  $2 \times 10^4$  Pa, and (3) the solubles (b) having an intrinsic viscosity  $[\eta]$  (in decalin at 135°C) of 3.3 dl/g or higher and an ethylene unit content of 43% by weight or smaller; (B) 0 to 10% by weight of a rubber-like elastomer; and (C) 10 to 30% by weight of talc. The automotive interior trims are produced by injection-molding the composition.



# Declaration and Power of Attorney For Patent Application

## 特許出願宣言書及び委任状

### Japanese Language Declaration

#### 日本語宣言書

下記の氏名の発明者として、私は以下の通り宣言します。

私の住所、私書箱、国籍は下記の私の氏名の後に記載された通りです。

下記の名称の発明に関して請求範囲に記載され、特許出願している発明内容について、私が最初かつ唯一の発明者（下記の氏名が一つの場合）もしくは最初かつ共同発明者（下記の名称が複数の場合）であると信じています。

上記発明の明細書は、

- ☐ 本書に添付されています。
- ☐ \_\_\_\_月\_\_\_\_日に提出され、米国出願番号または特許協定条約国際出願番号を\_\_\_\_とし、  
(該当する場合) \_\_\_\_に訂正されました。

私は、特許請求範囲を含む上記訂正後の明細書を検討し、内容を理解していることをここに表明します。

私は、連邦規則法典第37編第1条56項に定義されるとおり、特許資格の有無について重要な情報を開示する義務があることを認めます。

As a below named inventor, I hereby declare that:

My residence, post office address and citizenship are as stated next to my name.

I believe I am the original, first and sole inventor (if only one name is listed below) or an original, first and joint inventor (if plural names are listed below) of the subject matter which is claimed and for which a patent is sought on the invention entitled.

PROPYLENE-BASED RESIN COMPOSITION

AND AUTOMOTIVE INTERIOR TRIM

the specification of which

- ☐ is attached hereto.
- ☒ was filed on March 08, 2000  
as United States Application Number or  
PCT International Application Number  
PCT/JP00/01386 and was amended on  
\_\_\_\_ (if applicable).

I hereby state that I have reviewed and understand the contents of the above identified specification, including the claims, as amended by any amendment referred to above.

I acknowledge the duty to disclose information which is material to patentability as defined in Title 37, Code of Federal Regulations, Section 1.56.

Japanese Language Declaration  
(日本語宣言書)

私は、米国法典第35編119条 (a) - (d) 項又は365条 (b) 項に基づき下記の、米国以外の国の少なくとも一カ国を指定している特許協力条約365 (a) 項に基づく国際出願、又は外国での特許出願もしくは発明者証の出願についての外国優先権をここに主張するとともに、優先権を主張している、本出願の前に出願された特許または発明者証の外国出願を以下に、枠内をマークすることで、示しています。

Prior Foreign Application(s)

外国での先行出願

63398/1999

(Number)  
(番号)

Japan

(Country)  
(国名)

(Number)  
(番号)

(Country)  
(国名)

私は、第35編米国法典119条 (e) 項に基づいて下記の米国特許出願規定に記載された権利をここに主張いたします。

(Application No.)  
(出願番号)

(Filing Date)  
(出願日)

私は、下記の米国法典第35編120条に基づいて下記の米国特許出願に記載された権利、又は米国を指定している特許協力条約365条 (c) に基づく権利をここに主張します。また、本出願の各請求範囲の内容が米国法典第35編112条第1項又は特許協力条約で規定された方法で先行する米国特許出願に開示されていない限り、その先行米国出願書提出日以降で本出願書の日本国内または特許協力条約国際提出日までの期間中に入手された、連邦規則法典第37編1条56項で定義された特許資格の有無に関する重要な情報について開示義務があることを認識しています。

(Application No.)  
(出願番号)

(Filing Date)  
(出願日)

(Application No.)  
(出願番号)

(Filing Date)  
(出願日)

私は、私自信の知識に基づいて本宣言書中で私が行なう表明が真実であり、かつ私の入手した情報と私の信じるところに基づく表明が全て真実であると信じていること、さらに故意になされた虚偽の表明及びそれと同等の行為は米国法典第18編第1001条に基づき、罰金または拘禁、もしくはその両方により処罰されること、そしてそのような故意による虚偽の声明を行なえば、出願した、又は既に許可された特許の有効性が失われることを認識し、よってここに上記のごとく宣誓を致します。

I hereby claim foreign priority under Title 35, United States Code, Section 119 (a)-(d) or 365(b) of any foreign application(s) for patent or inventor's certificate, or Section 365(a) of any PCT International application which designated at least one country other than the United States, listed below and have also identified below, by checking the box, any foreign application for patent or inventor's certificate, or PCT International application having a filing date before that of the application on which priority is claimed.

Priority Claimed  
優先権主張

10/03/1999

(Day/Month/Year Filed)  
(出願年月日)

(Day/Month/Year Filed)  
(出願年月日)

☒

Yes  
はい

☐

Yes  
はい

☐

No  
いいえ

☐

No  
いいえ

I hereby claim the benefit under Title 35, United States Code, Section 119(e) of any United States provisional application(s) listed below.

(Application No.)  
(出願番号)

(Filing Date)  
(出願日)

I hereby claim the benefit under Title 35, United States Code, Section 120 of any United States application(s), or Section 365(c) of any PCT International application designating the United States, listed below and, insofar as the subject matter of each of the claims of this application is not disclosed in the prior United States or PCT International application in the manner provided by the first paragraph of Title 35, United States Code Section 112, I acknowledge the duty to disclose information which is material to patentability as defined in Title 37, Code of Federal Regulations, Section 1.56 which became available between the filing date of the prior application and the national or PCT International filing date of application.

(Status: Patented, Pending, Abandoned)  
(現況: 特許許可済、係属中、放棄済)

(Status: Patented, Pending, Abandoned)  
(現況: 特許許可済、係属中、放棄済)

I hereby declare that all statements made herein of my own knowledge are true and that all statements made on information and belief are believed to be true; and further that these statements were made with the knowledge that willful false statements and the like so made are punishable by fine or imprisonment, or both, under Section 1001 of Title 18 of the United States Code and that such willful false statements may jeopardize the validity of the application or any patent issued thereon.

## Japanese Language Declaration

(日本語宣言書)

委任状：私は下記の発明者として、本出願に関する一切の手続きを米特許商標局に対して遂行する弁理士または代理人として、下記の者を指名いたします。

(弁理士、または代理人の指名及び登録番号を明記のこと)

POWER OF ATTORNEY: As a named inventor, I hereby appoint the following attorney(s) and/or agent(s) to prosecute this application and transact all business in the Patent and Trademark Office connected therewith: (list name and registration number)

Norman F. Oblon, Reg. No. 24,618; Marvin J. Spivak, Reg. No. 24,913; C. Irvin McClelland, Reg. No. 21,124; Gregory J. Maier, Reg. No. 25,599; Arthur I. Neustadt, Reg. No. 24,854; Richard D. Kelly, Reg. No. 27,757; James D. Hamilton, Reg. No. 28,421; Eckhard H. Kuesters, Reg. No. 28,870; Robert T. Pous, Reg. No. 29,099; Charles L. Gholz, Reg. No. 26,395; William E. Beaumont, Reg. No. 30,996; Jean-Paul Lavalleye, Reg. No. 31,451; Stephen G. Baxter, Reg. No. 32,884; Richard L. Treanor, Reg. No. 36,379; Steven P. Weihrouch, Reg. No. 32,829; John T. Goolkasian, Reg. No. 26,142; Richard L. Chinn, Reg. No. 34,305; Steven E. Lipman, Reg. No. 30,011; Carl E. Schlier, Reg. No. 34,426; James J. Kulbaski, Reg. No. 34,648; Richard A. Neifeld, Reg. No. 35,299; J. Derek Mason, Reg. No. 35,270; Surinder Sachar, Reg. No. 34,423; Christina M. Gadiano, Reg. No. 37,628; Jeffrey B. McIntyre, Reg. No. 36,867; William T. Enos, Reg. No. 33,128; Michael E. McCabe, Jr., Reg. No. 37,182; Bradley D. Lytle, Reg. No. 40,073; and Michael R. Casey, Reg. No. 40,294, with full powers of substitution and revocation.

書類送付先

Send Correspondence to:

OBLON, SPIVAK, MCCLELLAND, MAIER &amp; NEUSTADT, P.C.

FOURTH FLOOR

1755 JEFFERSON DAVIS HIGHWAY

ARLINGTON, VIRGINIA 22202 U.S.A.

直接電話連絡先：(名前及び電話番号)

Direct Telephone Calls to: (name and telephone number)

(703) 413-3000

単独発明者または第一の共同発明者の氏名	1-00	Full name of sole or first joint inventor
発明者の署名	日付	Ryuzo TOMOMATSU
住所		Inventor's signature Date
国籍		Ryuzo Tomomatsu 03/10/2000
郵便の宛先		Residence
		Chiba-ken, Japan JPX
		Citizenship
		Japan
		Post Office Address
		1-1, Anesakikaigan, Ichihara-shi, Chiba-ken, Japan
第二の共同発明者の氏名	2-00	Full name of second joint inventor, if any
第二の共同発明者の署名	日付	Youichi MATSUO
住所		Second joint Inventor's signature Date
国籍		Youichi Matsuo 03/10/2000
郵便の宛先		Residence
		Chiba-ken, Japan JPX
		Citizenship
		Japan
		Post Office Address
		1-1, Anesakikaigan, Ichihara-shi, Chiba-ken, Japan

(第三以降の共同発明者についても同様に記載し、署名すること)

(Supply similar information and signature for third and subsequent joint inventors.)

# Japanese Language Declaration

(日本語宣言書)

第三の共同発明者の氏名	3-00	Full name of third joint inventor, if any Naoki NARUKAWA
第三の共同発明者の署名	日付	Third joint Inventor's signature Naoki Narukawa Date 03/10/2000
住所		Residence Chiba-ken, Japan JPX
国籍		Citizenship Japan
郵便の宛先		Post Office Address 1-1, Anesakikaigan, Ichihara-shi, Chiba-ken, Japan

第四の共同発明者の氏名	4-00	Full name of fourth joint inventor, if any Tetsushi YAMADA
第四の共同発明者の署名	日付	Fourth joint Inventor's signature Tetsushi Yamada Date 03/10/2000
住所		Residence Saitama-ken, Japan JPX
国籍		Citizenship Japan
郵便の宛先		Post Office Address c/o Kabushiki Kaisha Honda Gijutsu Kenkyusho 4-1, Chuo 1-chome, Wako-shi, Saitama-ken, Japan

第五の共同発明者の氏名	5-00	Full name of fifth joint inventor, if any Tetsuya ODA
第五の共同発明者の署名	日付	Fifth joint Inventor's signature Tetsuya Oda Date 03/10/2000
住所		Residence Saitama-ken, Japan JPX
国籍		Citizenship Japan
郵便の宛先		Post Office Address c/o Kabushiki Kaisha Honda Gijutsu Kenkyusho 4-1, Chuo 1-chome, Wako-shi, Saitama-ken, Japan

第六の共同発明者の氏名		Full name of sixth joint inventor, if any
第六の共同発明者の署名	日付	Sixth joint Inventor's signature Date
住所		Residence
国籍		Citizenship
郵便の宛先		Post Office Address

(第六またはそれ以降の共同発明者に対しても同様な情報および署名を提供すること。)

(Supply similar information and signature for third and subsequent joint inventors.)